



TECHNICAL DATA SHEET		
Specifications		
Code	600401	
Description	Filter paper	
Technical data		
Composition	Paper	
Recommended air velocity	0,50 - 1,00	m/s
Pressure drop		
0,50 m/s	20	Pa
0,75 m/s	30	Pa
1,00 m/s	40	Pa
Max. recommended pressure drop	128 (possible up to 256)	Pa
Load		
Lacquers	10	kg/m²
High solids	12	kg/m²
Polyester	13	kg/m²
Efficiency		
Lacquers	93,1	%
High solids	98,2	%
Polyester	97,8	%
Functional data		
Flammability	Burns with difficulty	
Properties		
Brown color		
2 layers of "kraft" paper, punched, pleated and glued together		

The above mentioned data have been determined according to the averages obtained from a series of typical results and are intended just for reference. The technical information is subject to changes, usual tolerances apply.